

## MATERIAL SPECIFICATION

### Barrier Foil Laminate

### NIP3075PE

PET12 // AI9 // LDPE75

Properties	Unit	Method	Value
Thickness	µm		101
Unit weight	g/m <sup>2</sup>		115
Max width	mm		1200
<b>Adhesive system LK427</b>			
- amount per layer	g/m <sup>2</sup>		2.0-3.0
- peel strength	N/m	IPC-TM-650; 2.4.9	1000
<b>Physical and Thermal properties</b>			
Tensile strength of laminate, max load (MD) (TD)	N/mm <sup>2</sup>	IPC-TM-650; 2.4.19c	47
			42
Elongation at break (MD) (TD)	%	IPC-TM-650; 2.4.19c	60
			57
Bursting strength	kN/m <sup>2</sup>	ISO 2578:2001	421
Tearing resistance (MD) (TD)	mN	ISO 1974:1990	800
			1205
<b>Permeability</b>			
WVTR	ml/m <sup>2</sup> /24 hrs	ASTM F 1249-05	<0.005
O <sub>2</sub> permeability	ml/m <sup>2</sup> /24 hrs	ASTM D 3985-05	<0.05

This information is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose. Use of Skultuna Flexible's materials in your particular application may yield different results.

Issue date: 2010-05-25/0

Data and product description have to be considered indicative. The information on the data sheet is liable to change due to innovation and improvement in the manufacturing process. We assume no liability for any infringement of patent, copyright or design on the part of the customer while exploiting the laminate for different end-uses.